



Breathable Membranes for Rainscreen Wall and Sloped Roof Systems

SRP 60 UV Seam Seal Tape

Basic Use

Use **SRP 60 UV** Seam Seal Tape to seal all seams between layers of SRP Breather Membranes and to join to other wall components such as and including windows, penetrations and terminations. SRP 60 UV Seam Seal Tape creates moisture tight, air and vapour barrier. SRP 60 UV Seam Seal Tape bonds to a wide range of surfaces including: glass, wood, aluminum, vinyl, OSB, polyethylene, polypropylene, polystyrene, fiberglass, brick, concrete, masonry, and most construction materials. Confirm adhesion through a field test.

SRP 60 UV Seam Seal Tape is designed to be used with AirOutshield UV for open jointed cladding systems and is compatible with all SRP AirOutshield membranes.

Composition

Adhesive carrier: PE-foil, reinforced with polyester threads
Adhesive type: Acrylate-dispersion, solvent free
Liner: Silicone paper

Technical Data

Total thickness without liner: 0.320 mm
Peel adhesion: 30 N / 25 mm (AFERA 5001)
Temperature resistance (short-term): - 40 °C / + 80 °C
Outdoor Exposure: 2 years
Shelf life: 1 year (original packed rolls only)

Width of roll: 60 mm
Length of roll: 25 m (82 ft.)
Rolls per case: 5
Total length per case: 125m (410 ft.)
Weight per case: 3.9kg (8.7 lbs)

Surface Preparation

Surface must be clean and dry. Moisture, dust, dirt, or other foreign matter should be removed. Remove oil and grease, etc. with a suitable cleaner.

Application

Install SRP 60 UV Seam Seal Tape centered over the seam, removing the release liner gradually to prevent contamination of the adhesive prior to application. Rub or roll with pressure using your hand or a steel roller to activate bonding process. This material may be applied to clean dry surfaces from 100 F to 32 F ambient.

Warranty

The information, and in particular, the recommendations relating to the application and end-use of SRP Canada products, are given in good faith based on SRP Canada's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Technical Data Sheet for the product concerned, copies of which will be supplied on request or can be accessed in the Internet under www.srpcanada.ca.

Issued: 2014-03-14

SRP Canada Inc.

www.srpcanada.ca

1-866-533-0233

Updated 2014-03-14